

Technical Data Sheet (TDS)

Product Description

Endura Adhesion promoter P-Link is designed to achieve excellent adhesion on Polypropylene.

Product features:

- Fast drying
- Excellent hold out
- Non-corrosive
- Solvent-base
- Easy to use

Suitability

Endura P-Link can be applied over polypropylene to achieve excellent adhesion between a polypropylene substrate and EX-2C Topcoat.

Product Characteristics

Volume Solids: 4% ± 1%

Shelf Life Single Component*: 2 years

*For unopened product

Surface Preparation

Surface must be washed and cleaned.

Mix Ratio

Endura P-Link is ready to spray. No reduction is necessary.

Application Method

Apply one thin wet coat. Topcoat can be applied as soon as the primer has been dried.

Cover Rate

Approximately 300 ft²/0.2 mils/gal

Dry Time

Dry to topcoat: 30 – 60 minutes at room temperature.

Ordering Information (sizing)

Available in Quart, Gallon and Pails. Other custom sizes may be available.

Quart [FAD0013-020]

Gallon [FAD0013-030]

Pail [FAD0013-050]

Safety Precautions

Please refer to all Safety Data Sheets (SDS) before using this product. SDS sheets can be found on our website at www.endura.ca.